



SKANDIA, Inc.

5181 Falcon Road • Rockford, Illinois 61109 • Phone 815/227-1611 • Fax 815/227-1920

Client:

Division of P.A. Grinnell Company
P.O. Box 985 • Mooresville, NC 28115
Phone (704) 662-9099 • Fax (704) 662-9109

WO #: 25866-98

Date: 10/22/98

Test Plan #:

PO #:

Aircraft:

STOCK

S/N:

NA

HORIZONTAL FLAMMABILITY TEST RESULTS

FAR 23.853 (a)

Conditioning Room: Time In: 10/21/98 9:00AM Time Out: 10/22/98 11:00AM

Specimen Desc.: P.A. GRINNELL CO.: COMPOSITE, WHITE GLASS/GRAY SILICONE, BATCH #23086

Specimen	Flame Application (Seconds)	Flame Time (Minutes)	Burn Length (Inches)	Burn Rate (Inch/Min)
#1	15	0.0	0.0	0
#2	15	0.0	0.0	0
#3	15	0.0	0.0	0
Average:		0.0	0.0	0

Comments:

Horizontal (15 sec.) Burn Test: 23.853(a) and 25.853(a) Appendix F Part I (a) (1) (v) Average Burn Rate Per Minute may not exceed 4". 25.853(a) Appendix F Part I (a) (1) (iv) Average Burn Rate Per Minute may not exceed 2.5".

Passed FAR:

Yes


No

Self Extinguished:

Yes

No

Signed:


Judy Boggs